



ONE-COMPONENT POLYURETHANE ADHESIVE FOAM.



PRODUCT DESCRIPTION

PU FOAM ADHESIVE is a one-component expanding foam contained in a pressurized spray can with a hand lever to feed the product. The extruded products expand upon contact with the humidity in the air and then harden rapidly to form a stable, closed-cell structure with excellent mechanical characteristics and high insulating and soundproofing properties. PU FOAM ADHESIVE is waterproof and are resistant to temperatures from -40°C to $+90^{\circ}\text{C}$, humidity and the effect of ageing. Both types of foam adhere well to all materials normally used in the building industry such as brickwork, concrete, gypsum, wood, metal, glass, foam polystyrene, PVC and rigid foam polyurethane, and are also resistant to the formation of mould and mildew. Once hardened, can be cut, sanded, ground, drilled, skimmed with cementitious products and painted. According to DIN 4102 German standards they are classified as flammability class B3.

FIELD OF APPLICATION

- Bonding non-structural building components.
- Fastening support frames in place for door and window fittings.

- Bonding bricks and pre-cast engineered blocks.
- Bonding EPS, XPS and mineral wool panels in external insulation systems.
- Bonding encased electrical fittings such as cable-runs and junction boxes, including in plasterboard walls.

SUITABLE SUBSTRATES

- Plastic
- Concrete
- Bricks
- Wood
- EPS Panel
- Thermal Insulation Panels
- Metallic surfaces.

LIMITATIONS

- Do not use on surfaces with traces of oil, grease or stripping compound.
- Do not use at temperatures lower than $+5^{\circ}\text{C}$.
- Not suitable for compressive stress, tensile stress or continuous or snap shear stresses.

APPLICATION PROCEDURE

A) Preparation of substrate

The surface on which the foam is to be applied must have no traces of dust, must be clean with no grease or oil stains and any loose or detached material must be removed. Protect delicate surfaces next to the area where the product is being applied with masking tape to prevent the product going onto them.

B) Preparing the product

Ready to be used.

C) Applying the product

PU FOAM ADHESIVE (manual application)
Remove the protective cap and screw the feed tube to the spray nozzle. Hold the can upside down, point the tube to the area where the foam is to be applied and press the hand lever. Feed the foam into the area starting from the lowest, deepest part and work upwards until the gap is filled to around 50-60% of its volume. The gap will become completely filled when the material has expanded.

PU FOAM ADHESIVE (gun application)
Screw the can to the adaptor gun using the threaded collar. Point the gun towards the area to be filled and press the trigger. The amount of foam to be fed into the area may be regulated with the feed screw located at the back of the gun and by the stroke of the trigger. Feed the foam into the area starting from the lowest, deepest part and work upwards until the gap is filled to around 50-60% of its volume. The gap will become completely filled when the material has expanded. If the can runs out, replace it immediately with a new one; shake well prior to use to prevent the foam setting inside the gun. To fill larger gaps (more than 5 cm wide), we recommend applying several layers of product; wait between each layer until the previous one has expanded before applying the next one. Immediately after

applying the product, we recommend spraying the foam with water to get a better yield and optimum polymerization.

COVERAGE / CONSUMPTION

A can of 750 ml can yield up to 45Lt volume.

PACKAGING

PU FOAM ADHESIVE is supplied in:
– 750ml can.

SHELF LIFE-STORAGE

Original sealed packaging of this product is guaranteed to be of first quality for 18 months if stored in a dry area and temperatures between +5oC and +35oC.

SAFETY INSTRUCTION

PU FOAM ADHESIVE is flammable. It is recommended to keep it away from naked flames and sparks, to avoid smoking, to prevent the build-up of electrostatic charges and to work in well ventilated areas. During use wear protective gloves and goggles and take the usual precautions for the handling of chemicals. If the product comes in contact with the eyes or skin, wash immediately with plenty of water and seek medical attention. Furthermore, is hazardous for aquatic life, do not dispose of the product in the environment. For further and complete information about the safe use of our product please refer to the latest version of our Safety Data Sheet. **PRODUCT FOR PROFESSIONAL USE.**

TECHNICAL DATA

Product identity

Consistency	cream
Color	Yellow
Density (kg/m ³)	800

Application data (at +23°C and 50% R.H.)

Dilution	Ready to used
Initial drying	7 minutes
Complete drying	2-4 minutes
Hardening time	30 minutes
Service temperature range	-40°C to +100°C
Application temperature	+5°C to +35°C
Compressive strength	7.5 N / cm ²
Elongation	30%
Density after hardening	20 Kg / m ³
Thermal conductivity	0.035 W / mK
Water resistance	excellent
Atmospheric agent resistance	excellent



+1 55 12 258 428
info@dc-industries.us
www.dc-industries.us