



SEAL MASTER RAPID IS A TWO-COMPONENT FLEXIBLE CEMENTITIOUS WATERPROOF SLURRY COMPRISING A LIQUID POLYMER AND CEMENT-BASED POWDER.



PRODUCT DESCRIPTION

Seal Master Rapid is a two-component flexible cementitious waterproof slurry comprising a liquid polymer and cement-based powder. When are mixed and applied after curing, it forms a flexible, continuous waterproofing membrane. The product protects cement-based plasters and concrete, including those on grade. Seal Master Rapid meets the requirements defined by EN 1504-2 coating (C) according to the PI, MC, and IR principles ("Protection systems for concrete surfaces").

FIELD OF APPLICATION

- Interior and exterior use.
- For waterproofing before installing all types of tile and stone.
- Swimming pools, fountains, and water features.
- Terraces and balconies over unoccupied spaces.
- Restoring old balconies without removing the existing floor.
- Shower pans, stalls, and tub surround.
- As a flexible leveling compound subject to vibrations or movement on the concrete.
- Protection of concrete from aging and carbonation.
- Protection of concrete on grade.
- Flexible leveling over plasters and screeds with micro cracks.
- Seal Master Rapid is completely water-resistant against positive water pressure and is water-resistant against negative water pressure of up to 1.5 atm. Once it is cured, it is resistant to soluble salts present in seawater or the ground, such as chlorides and sulfates.

SUITABLE SUBSTRATES

- Concrete
- Cement Mortar Bed
- Cement Mortar
- Cement Plaster/Render
- Concrete Masonry
- Masonry
- Cement Backer Board
- Ceramic Tile and Stone.

LIMITATIONS

- Do not mix with other cement or components.
- Do not apply on metallic or rubber substrate.
- Do not apply on not sufficient cured substrate.
- Do not apply over 4 mm thicknesses per coat.
- Do not apply in temperatures above 40°C and below +5°C.
- It must be protected from rain or bad weather for at least 24 hours after application.
- Avoid direct sunlight during application.
- Prime highly absorbent surfaces to improve adhesion.
- In case of negative water pressure can lead to delamination during frost conditions
- Always apply at least two layers, making sure to wait until the previous layer is dry before applying the next.

APPLICATION PROCEDURE

A) Preparing the substrate

All substrates must be mechanically strong, free of dirt, oil, grease, paint, laitance, concrete sealers, efflorescence, or curing compounds. Any grease or wax must be removed from old ceramic floors using a basic detergent. Screeds and concrete must be completely cured, at least 30 days for screeds and 3 months for concrete. Prime highly absorbent surfaces like lightweight concrete with Seal Primer or DCI Grip Primer to improve adhesion. For exterior applications, always maintain expansion joints from the substrate and treat with DCI Tape W12. For all coves, corners, columns, expansion joints, floor/wall transitions, and other changes in substrate plane, treat with appropriate TAPE before application of Seal Master Rapid.

B) Preparing the product

Pour the B component (liquid) into a suitable, clean container, then slowly add the A component (powder) while stirring with a mechanical mixer making sure that no powder remains stuck on the bottom or to the sides of the container. Continue stirring until a homogenous mixture is formed. Use a low-speed mechanical mixer for this preparation to avoid too much air being dragged into the mix. Do not prepare the mix by hand. Preparation of Seal Master Rapid can also be made with a mortar mixer, which is usually connected with the mortar sprayer. In this case, make sure that the mixture is homogenous before it is poured into the pump's hopper.

C) Applying the product

Apply Seal Master Rapid within 60 minutes after preparation. Applied on the prepared surface to a feather edge with a thin layer of Seal Master Rapid with a smooth trowel or brush; then, while the first coat is still fresh, apply a second coat to form a final thickness of at least 2 mm thick. In the case of waterproofing terraces, balconies, basins, and swimming pools, we recommend embedding alkali-resistant reinforcement mesh in the first layer of Seal Master Rapid while it is still fresh.

The mesh must be used in areas with either small cracks or regions under particular stress. After installing the mesh, finish off the surface with a flat trowel and apply a second layer of Seal Master Rapid when the first one has set (after 4-5 hours). After applying Seal Master Rapid, wait 5 days for curing before laying ceramic tiles.

D) Installing the tiles

Wait approx one day after applying Seal Master Rapid before installing tiles and using a C2 adhesive.

COVERAGE / CONSUMPTION

The consumption is approximately 3 - 4 kg/m² at 2.5 - 3 mm thickness.

PACKAGING

Seal Master Rapid is supplied in:

- 25 kg paper bags COMP. A
- 10 kg plastic canisters COMP. B

SHELF LIFE-STORAGE

Original sealed packaging of this product is guaranteed to be of first quality for 12 months. Areas with high humidity will reduce the shelf life of the bagged product.

SAFETY INSTRUCTION

SEAL MASTER RAPID contains cement that, when in contact with sweat or other body fluid, causes allergic reactions to those predisposed and an irritant alkaline reaction. It can cause damage to the eyes. During the usage, wear protective gloves and goggles and take the usual precautions for handling chemicals. When in contact with skin or eyes, wash immediately with plenty of water and seek medical attention.

TECHNICAL DATA

Product identity

	Component A	Component B
Consistenza	powder	liquid
Colore	white and grey	White
Densità apparente (kg/m ³)	1250	1050
Dry solids content (%)	100	50
Classification Standard	EN 1504-2	EN 14891

Application data (at +23°C and 50% R.H.)

Mix ratio	25 parts SEAL MASTER RAPID A with 10 parts SEAL MASTER RAPID B by weight
Consistency of mix	Liquid pasty
Density of mix (kg/m ³):	1650
pH of the mix	13
Pot life	over 1 hour
Application temperature	+5°C a +40°C

Final performances

Adhesion strength to concrete according EN 1542:	
- Adhesion strength after 28 days at +20°C and 50% R.H. (N/mm ²):	1.6
- Adhesion strength after 7 days at +20°C and 50% R.H. + 21 days in water (N/mm ²):	0.9
Thermal compatibility to freeze/thaw cycles, according to EN 1542 (N/mm ²):	1.87
Flexibility according to DIN 53504 expressed as elongation:	
- Flexibility after 28 days at +20°C and 50% R.H. (%):	60
Static crack-bridging at -20°C according EN 1062-7 expressed as the maximum width of the crack (mm):	class A3
Dynamic crack-bridging at -20°C according EN 1062-7 of a film of SEAL MASTER RAPID reinforced with fiber mesh, expressed as resistance to cracking cycles: classB3.1(-20°C) No Fail	
Impermeability to water expressed as capillary water absorption according EN 1062-3 (kg/m ² .h0.5):	< 0.03
Permeability to carbon dioxide (CO ₂) according EN 1062-6	
- diffusion in an equivalent thickness of air SDCO ₂ (m):	> 50
Crack-bridging ability at +20°C according EN 14891-A.8.2 (mm):	2.2
Crack-bridging ability at -20°C according EN 14891-A.8.3 (mm):	0.9
Initial bond strength according to EN 14891-A.6.2 (N/mm ²):	1.6
Adhesion strength after immersion in water according to EN 14891-A.6.3 (N/mm ²):	1.64
Adhesion strength after application of heat source according to EN 14891-A.6.5 (N/mm ²):	1.84
Adhesion strength after freeze-thaw cycles according to EN 14891-A.6.6 (N/mm ²):	1.25
Adhesion strength after immersion in basic water according to EN 14891-A.6.9 (N/mm ²):	0.9

WARNING

Danger. Contains Portland Cement: Chromium VI < 2 ppm within the validity period of the product. H315 Causes skin irritation. H317 May cause an allergic skin reaction. H318 Causes serious eye damage. H335 May cause respiratory irritation. P261 Avoid breathing dust. P280 Wear protective gloves/protective clothing/eye protection/face protection. P302 + P352 IF IN CONTACT WITH YOUR SKIN: Wash with plenty of water/... P305 + P351 + P338 IF IN CONTACT WITH YOUR EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. P310 Immediately call a POISON CENTER/doctor/...



+1 55 12 258 428
info@dc-industries.us
www.dc-industries.us