

## **SPECIFICATIONS**

## **CFW 200**

Is a bidirectional carbon fiber fabric with balanced weight, characterized by high modulus of elasticity and very high tensile strength that can be placed using two different methods:

- · wet system;
- · dry system.

by using the following range of epoxy resins:

- · Epo Primer ST, suggested for the strengthening of the substrate.
- $\cdot$  CF W2, recommended for the leveling of surfaces with a roughness equal or greater than  $\pm\,2$  mm.

## **TECHNICAL DATA**

## **Product identity**

Tensile strength (MPa) 2800 Modulus of elasticity (GPa) 163 Ultimate strain (%) 1,60 Density (g/cm3) 1,60