



PREMIUM, ACRYLIC, TEXTURED TOP COATING FOR SPORTIVE FLOORS.



PRODUCT DESCRIPTION

Extracoat SF 200 is a flexible, acrylic topcoat. It is used on indoor and outdoor surfaces for tennis, pickleball and basketball courts as well as for multipurpose areas. Extracoat SF 200 is combined with sportive floor system products to form durable and comfortable playing surfaces.

FIELD OF APPLICATION

- As a finish coat for indoor and outdoor applications for sportive floors
- As a finish coat to renew existing acrylic or urethane surfaces.

SUITABLE SUBSTRATES

- Cured concrete
- Cured asphalt

LIMITATIONS

- Concrete floors must be completely cured and free from hydrostatic pressure and alkaline conditions.
- Do not install when the moisture vapor emission rate of the concrete substrate exceeds 8 lbs.
- Do not install when relative humidity of the concrete substrate exceeds 85%.
- Do not apply when rain is imminent.
- Do not apply over damp or wet surfaces.
- Apply only when the surface temperature is between 10°C and 60°C.
- Do not apply if the ambient temperature is lower than 10°C.
- Do not apply if the level of ambient humidity is higher than 85%.

APPLICATION PROCEDURE

A) Preparation of substrate

Substrate must be clean and free of dust, dirt, oil, grease, paint, curing agents, concrete sealers, loosely bonded toppings, loose particles, old coating residues, and any other substance or condition that may prevent or reduce adhesion.

B) Preparing the product

Extracoat SF 200 must be diluted with water up to 20% according to the application method used. The use of a low-speed mechanical mixer is recommended. The mixture should be stirred until it reaches a homogeneous consistency. It is important to keep the mixture homogeneous by occasional remixing during the application process.

C) Applying the product

Pour the product on the surface of the floor and spread it out evenly with a smooth trowel or flexible rubber squeegee.

COVERAGE / CONSUMPTION

The consumption of EXTRACOAT SF 200 depends on the absorption and porosity of the substrate. Typical consumption is between 400 and 600 gr/m².

PACKAGING

Extracoat SF 200 is supplied in:

- 1 kg plastic can
- 5 kg plastic can
- 10 kg plastic can.

SHELF LIFE-STORAGE

Original sealed packaging of this product is guaranteed to be of first quality for 24 months if stored in a dry area. The high humidity will reduce the shelf life of the bagged product.

SAFETY INSTRUCTION

Extracoat SF 200 is not considered dangerous according to the current regulations regarding the classification of mixtures. However, it is recommended to wear protective clothes, gloves, and goggles and take the usual precautions for handling chemicals. For complete information about the safe use of our product, please refer to the latest version of our Safety Data Sheet. **PRODUCT FOR PROFESSIONAL USE.**

TECHNICAL DATA

Product identity	
Consistency	liquid pasty
Color	White and different colors
Density (kg/m ³)	1450
Dry solids content (%)	80



+1 55 12 258 428
info@dc-industries.us
www.dc-industries.us