

SPECIFICATIONS

EPO VARNISH-W45

Is a two-component, moisture-curing, non-yellowing, transparent aliphatic epoxy varnish. When Epo Varnish W-45 is mixed with clean, dry natural aggregates at the correct aggregate/binder ratio, it may be used to create surfaces with very high resistance to wear and yellowing. Preparation is very simple and consists of mixing assorted aggregates, such as marble, quartz or natural stone with particle size 2-4 mm or 4-8 mm with Epo Varnish W-45 and then placing the mix to form a multitude of decorative effects. What is more, its excellent resistance to atmospheric agents means it may also be used for external applications, particularly for pervious surfaces. Epo Varnish W-45 also resists the action of the most commonly used de-icing salts.

TECHNICAL DATA

Product identity

TECHNICAL DATA (typical values)

Colour: transparent, colourless

Consistency: liquid

Density (g/cm³): 1.15

Brookfield viscosity (mPa·s): 450

Dry solids content (%): 95