



FIBER-REINFORCED COMPENSATED-SHRINKAGE
MORTAR FOR REPAIRING CONCRETE AND ANCHO-
RING METAL STRUCTURES.



PRODUCT DESCRIPTION

Flow Grout C50 Rapid is a ready-mixed, compensated-shrinkage, powdered mortar made from high strength cement, selected aggregates, special super-plasticizing additives and synthetic fibers. When mixed with water, Flow Grout C50 Rapid forms hi-flow mortar suitable for pouring into formwork, when used to reintegrate concrete, or into specially prepared seats, when used for anchoring work, without having to vibrate the mix and with no risk of segregation, including when applied in thick layers. If Flow Grout C50 Rapid is mixed with water only, it must be cured in a damp environment in order to allow its expansive properties to develop fully and correctly. Thanks to this particular technology, guaranteeing higher dimensional stability and a reduction in cracking phenomenon. Flow Grout C50 Rapid complies with the principles defined in EN 1504-9, the requirements of EN 1504-3, which regulates products used to carry out structural and non-structural repairs on concrete elements, and of EN 1504-6, which defines products used to anchor rebar in place.

SUITABLE SUBSTRATES

- Concrete.

FIELD OF APPLICATION

- Structural reintegration of reinforced concrete pillars and beams by pouring the mortar into formwork.
- Repairing the lower spigots on pre-compressed viaduct beams.
- Reintegrating floor slabs after removing damaged areas by scarifying.
- Repairing concrete floors.
- Filling rigid joints between concrete elements.
- Anchoring metal structures.
- Footings for masonry.
- Anchoring machine tools by casting the mortar below and the machine base.
- Repairing concrete steps.

LIMITATIONS

- Do not apply on smooth substrates: roughen surfaces beforehand.
- Do not apply on dry substrates.
- Do not add cement or admixtures.
- Do not add water to the mix to make it more workable once it starts to set.
- Do not leave bags exposed to the sun before use.
- Do not use if the temperature is lower than +5°C.
- Do not use if the bag is damaged or if it has been opened previously.
- Do not use for fixing elements accurately in place.

APPLICATION PROCEDURE

A) Preparation of the substrate

- Remove all deteriorated and loose concrete to form a solid, rough and strong substrate. Any areas previously repaired and which are not perfectly bonded must also be removed.
- Remove all dust, rust, cement laitance, grease, oil and paint from the concrete and reinforcement rods by sandblasting or hydro-sandblasting.
- Treat reinforcement rods with Ferropri-mer 1K or 2K, according to the procedure given in the Technical Data Sheet of product.
- Saturate the substrate with water.
- Before carrying out repairs, wait until excess water has evaporated.

B) Preparing the product

Pour approximately 5.5 liters of clean water into a container and slowly add a 25 kg bag of Flow Grout C50 Rapid while mixing. Carefully mix the blend for several minutes then remove any powder which has stuck to the sides and bottom of the container. Add more water to obtain the consistency required without exceeding the recommended amount, approximately 6-6.5 liters. Mix again for several minutes to form a well-blended, plastic consistency, lump-free mixture. Flow Grout C50 Rapid remains workable for around 15 minutes at +10°C to +25°C.

C) Applying the product

Pour a constant flow of Flow Grout C50 Rapid into the formwork from one side only, making sure that the air is expelled and make sure the formwork is well sealed to prevent any mortar leaking out. The formwork must not draw any of the mixing water from the Flow Grout C50 Rapid and it is recommended to treat the formwork with a form-release product. There is no need to vibrate the mortar after pouring. Pieces of round bar may be used to help the mortar flow into more difficult areas. If areas thicker than 5 cm need to be repaired with Flow Grout C50 Rapid and they are not confined, dolly bars must be placed in position before pouring the mortar

so that the layer of mortar over them is at least 2-3 cm thick. Layers less than 5 cm thick may be poured without adding rebar, as long as the substrate has a surface roughness of at least 5 mm to contrast expansion phenomenon, which normally takes place within the first 24 hours. When applied as anchoring of metallic structures pour Flow Grout C50 Rapid in a constant flow from one side only, making sure that the air is expelled from the area to be filled, which must be at least 2.5-3 times bigger than the diameter of the bar to be anchored. The mortar does not need to be vibrated after pouring. Use lengths of round iron bar to work the mortar into tight spaces.

COVERAGE / CONSUMPTION

The consumption is approximately 1.5kg/m² at 1 mm thickness.

PACKAGING

Flow Grout C50 Rapid is supplied in:
– 25 kg paper bags.

SHELF LIFE-STORAGE

Original sealed bags of this product are guaranteed to be of first quality for 12 months if stored off of the ground in a dry area. High humidity will reduce the shelf life of the bagged product.

SAFETY INSTRUCTION

Flow Grout C50 Rapid is irritant; it contains cement that when in contact with sweat or other body fluid causes irritant alkaline reaction and allergic reactions to those predisposed. It can cause damage to eyes. In case of contact with eyes or skin wash immediately with plenty of water and seek medical attention. It is recommended to use protective gloves and goggles. For further and complete information about the safe use of our product please refer to the latest version of our Material Safety Data Sheet. **PRODUCT FOR PROFESSIONAL USE.**

TECHNICAL DATA

Product identity	
Class according to EN 1504-3	R4
Type	PCC
Consistency	powder
Color	grey
Maximum diameter of aggregate (EN 1015-1) (mm)	2.5
Bulk density (g/cm ³)	1.400
Dry solids content (%)	100
Ion chloride content (%)	≤ 0.05
Application data (at +23°C and 50% R.H.)	
Colour of mix	grey
Mixing ratio	26-28%
Consistency of mix	flow
Density of mix (kg/m ³)	2.400
pH of mix	12
Application temperature	from +5°C to +35°C
Pot life of mix	approx. 60 minutes
Waiting time before finishing with float	approx. 30 minutes
Setting time	approx. 30 minutes
Final performances	
Compressive strength (MPa)	55
Flexural strength (MPa)	11
Compressive modulus of elasticity (GPa)	27
Pull-out strength of steel bars - bonding stress - (MPa)	24
Bond strength on concrete (substrate type MC 0.40) according to EN 1766 (MPa)	≥ 2
Thermal compatibility measured as bond strength according to EN 1542 (MPa)	≥ 2
Capillary absorption (kg/m ² .h)	≤ 0.4
Impermeability expressed as coefficient of permeability to free water (kg/m ² .h)	W < 0.1 Class III
Permeability to water vapour – equivalent air thickness S - (m)	S < 5 Class I
Reaction to fire	A1

WARNING

Danger. Contains Portland Cement: Chromium VI < 2 ppm within the validity period of the product. H315 Causes skin irritation. H317 May cause an allergic skin reaction. H318 Causes serious eye damage. H335 May cause respiratory irritation. P261 Avoid breathing dust. P280 Wear protective gloves/protective clothing/eye protection/face protection. P302 + P352 IF IN CONTACT WITH YOUR SKIN: Wash with plenty of water/... P305 + P351 + P338 IF IN CONTACT WITH YOUR EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. P310 Immediately call a POISON CENTER/doctor/...



+1 55 12 258 428
info@dc-industries.us
www.dc-industries.us